

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

## (19) World Intellectual Property Organization International Bureau





(43) International Publication Date 22 January 2004 (22.01.2004)

PCT

(10) International Publication Number WO 2004/007611 A1

(51) International Patent Classification?: C08K 5/523, 5/49

C08L 69/00,

(21) International Application Number: PCT/KR2002/001832

(22) International Filing Date:

30 September 2002 (30.09.2002)

(25) Filing Language:

Korean

(26) Publication Language:

English

(30) Priority Data: 2002/40373

11 July 2002 (11.07.2002) KR

- (71) Applicant (for all designated States except US): CHEIL INDUSTRIES INC. [KR/KR]; 290 Gongdan-dong, Gumi-shi, 730-710 Gyungsangbuk-do (KR).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): LIM, Jong Cheol [KR/KR]; Chemicals Division R & D Center, 332-2 Gocheon-dong, Uiwang-si, 437-711 Gyeonggi-do (KR). YANG, Sam Joo [KR/KR]; Chemicals Division R & D Center, 332-2 Gocheon-dong, Uiwang-si, 437-711 Gyeonggi-do (KR).

- (74) Agent: CHOI, Duk Kyu; 5th Floor Chunwoo Bldg., 736 Yoksam-dong, Gangnam-gu, 135-080 Seoul (KR).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

## Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: FLAME RETARDANT THERMOPLASTIC RESIN COMPOSITION

(57) Abstract: The flame retardant thermoplastic resin composition of the present invention comprises (A) 45-95 parts by weight of a polycarbonate resin; (B) 1-50 parts by weight of a rubber modified vinyl graft copolymer; (C) 0-50 parts by weight of a vinyl copolymer; (D) 1-30 parts by weight of a mixture of organic phosphorous compounds consisting of (d<sub>1</sub>) 1-50 % by weight of a oligomeric compound of cyclic phosphazene and (d<sub>2</sub>) 99-50 % by weight of an oligomeric phosphoric acid ester compound, per 100 parts by weight of the sum of (A), (B) and (C); and (E) 0.05-5 parts by weight of a fluorinated polyolefin resin per 100 parts by weight of the sum of (A), (B) and (C).

